

MACHINING CONDITIONS

RDMT 10T3 M0 – LT 3000

Catalog N°: M0002225

| Material Group | Gr. N° | VDI Group | Material Examples | Hardness | DOC [mm] | | Feed [mm/rev] | | V _c [m/min] | | Suggested Starting Parameters | | | |
|----------------|--------------------------------------|-----------|-------------------|----------------|----------|-----|---------------|------|------------------------|-----|-------------------------------|------|----------------|-----|
| | | | | | min | max | min | max | min | max | DOC | Feed | V _c | |
| P | Non Aligned | 1 | 1 | C35, Ck45, | 125 HB | 0.5 | 2.5 | 0.18 | 0.64 | 190 | 330 | 1 | 0.34 | 250 |
| | | | 2 | 1020, 1045, | 190 HB | 0.5 | 2.5 | 0.18 | 0.64 | 190 | 300 | 1 | 0.34 | 220 |
| | | | 3 | 1060, 28Mn6 | 250 HB | 0.5 | 2.5 | 0.18 | 0.64 | 190 | 250 | 1 | 0.34 | 200 |
| | Low Aligned | 2 | 4, 6 | 42CrMo4, | 180 HB | 0.5 | 2.5 | 0.15 | 0.5 | 150 | 210 | 1 | 0.3 | 180 |
| | | | 5, 7 | St50, Ck60, | 230 HB | 0.5 | 2.5 | 0.15 | 0.44 | 130 | 190 | 1 | 0.27 | 150 |
| | | | 6 | 4140, 4340, | 280 HB | 0.5 | 2.5 | 0.15 | 0.5 | 150 | 240 | 1 | 0.3 | 200 |
| | | | 8 | 100Cr06 | 350 HB | 0.5 | 2.5 | 0.15 | 0.44 | 130 | 170 | 1 | 0.27 | 140 |
| | High Aligned | 3 | 10 | X40CrMoV5, | 220 HB | 0.5 | 1.8 | 0.12 | 0.44 | 90 | 150 | 0.8 | 0.27 | 130 |
| | | | 10 | H13, M42, D3, | 280 HB | 0.5 | 1.8 | 0.12 | 0.44 | 90 | 130 | 0.8 | 0.27 | 120 |
| | | | 11 | S6-5-2, 12Ni19 | 320 HB | 0.5 | 1.8 | 0.12 | 0.36 | 60 | 110 | 0.8 | 0.24 | 100 |
| | | | 11 | | 350 HB | 0.5 | 1.8 | 0.12 | 0.36 | 60 | 90 | 0.8 | 0.24 | 80 |
| M | Austenitic | 4 | 14 | 304, 316, | 180 HB | 0.5 | 2.5 | 0.15 | 0.5 | 190 | 250 | 1 | 0.3 | 220 |
| | | | 14 | X5CrNi18-9 | 240 HB | 0.5 | 2.5 | 0.12 | 0.44 | 160 | 210 | 1 | 0.3 | 190 |
| | Duplex | 5 | 14 | X2CrNiN23-4, | 290 HB | 0.5 | 2 | 0.12 | 0.36 | 70 | 130 | 0.8 | 0.24 | 100 |
| | | | 14 | S31500 | 310 HB | 0.5 | 2 | 0.12 | 0.36 | 70 | 120 | 0.8 | 0.24 | 90 |
| | Ferritic & Martensitic | 6 | 12 | 410, X6Cr17, | 200 HB | 0.5 | 2.5 | 0.15 | 0.5 | 150 | 210 | 1 | 0.3 | 190 |
| | | | 13 | 17-4PH, 430 | 42 HRc | 0.5 | 2 | 0.15 | 0.4 | 90 | 150 | 0.8 | 0.24 | 130 |
| K | Grey | 7 | 15 | GG20, GG40, | 150 HB | 0.5 | 2.5 | 0.18 | 0.64 | 150 | 240 | 1 | 0.34 | 200 |
| | | | 15 | EN-GJL-250 | 200 HB | 0.5 | 2.5 | 0.18 | 0.64 | 150 | 220 | 1 | 0.34 | 180 |
| | | | 16 | | 250 HB | 0.5 | 2.5 | 0.18 | 0.64 | 150 | 190 | 1 | 0.34 | 160 |
| | Malleable & Nodular | 8 | 17, 19 | GG20, GG70, | 150 HB | 0.5 | 2.5 | 0.15 | 0.56 | 100 | 200 | 1 | 0.3 | 180 |
| | | | 17, 19 | 50005 | 200 HB | 0.5 | 2.5 | 0.15 | 0.56 | 100 | 180 | 1 | 0.3 | 150 |
| | | | 18, 20 | | 250 HB | 0.5 | 2.5 | 0.15 | 0.56 | 100 | 150 | 1 | 0.3 | 130 |
| S | Fe, Ni & Co based | 9 | 31, 32 | Incoloy 800 | 240 HB | 0.5 | 2 | 0.12 | 0.36 | 30 | 50 | 0.8 | 0.24 | 32 |
| | | | 33 | Inconel 700 | 250 HB | 0.5 | 2 | 0.12 | 0.36 | 30 | 50 | 0.8 | 0.24 | 30 |
| | | | 34 | Stellite 21 | 350 HB | 0.5 | 2 | 0.12 | 0.36 | 30 | 50 | 0.8 | 0.24 | 30 |
| | Ti based | 10 | 36 | TiAl6V4 | - | 0.5 | 2 | 0.12 | 0.36 | 30 | 60 | 0.8 | 0.24 | 40 |
| | | | T40 | - | 0.5 | 2 | 0.12 | 0.4 | 40 | 70 | 0.8 | 0.27 | 55 | |
| H | Steel | 11 | 38 | X100 CrMo13, | 45 HRc | 0.3 | 0.9 | 0.1 | 0.36 | 40 | 80 | 0.5 | 0.21 | 60 |
| | | | 38 | 440C, | 50 HRc | 0.3 | 0.7 | 0.1 | 0.32 | 40 | 70 | 0.4 | 0.19 | 55 |
| | | | 38 | G-X260NiCr42 | 55 HRc | 0.3 | 0.6 | 0.1 | 0.28 | 40 | 60 | 0.3 | 0.18 | 50 |
| | Chilled Cast Iron White Cast Iron | 12 | 40 | Ni-Hard 2 | 400 HB | 0.3 | 0.7 | 0.1 | 0.36 | 40 | 80 | 0.4 | 0.21 | 50 |
| 41 | | | G-X300CrMo15 | 55 HRc | 0.3 | 0.6 | 0.1 | 0.28 | 30 | 60 | 0.3 | 0.18 | 40 | |
| NF | Aluminium | 14 | 25 | AlSi12 | 130 HB | 0.5 | 2.5 | 0.18 | 0.64 | 200 | 400 | 1 | 0.38 | 280 |

