

DNMG 150404 NN LT 10 & LT 1000

Material Group		Gr. N°	VDI Group	Material Examples*	Hardness	D.O.C. [mm]		Feed [mm/rev]		Amax [mm²]	V _c [m/min]		Optimal cutting conditions		
						min	max	min	max		min	max	D.O.C.	Feed	V _c
Steel	Non-alloyed	1	1	C35, Ck45, 1020,	125 HB	0.2	3.0	0.11	0.23	0.60	180	330	2.0	0.18	300
			2	1045, 1060, 28Mn6	190 HB		2.5		0.22	0.52		280			260
			3		250 HB		2.5		0.20	0.48		250			240
	Low alloyed	2	6	42CrMo4, St50,	180 HB	0.2	2.5	0.10	0.20	0.50	120	280	2.0	0.15	260
			4,6	Ck60, 4140, 4340, 100Cr6	230 HB		2.5		0.20	0.48		250			240
			5,7		280 HB		2.0		0.18	0.40		210			200
			8		350 HB		2.0		0.18	0.36		180			180
	High alloyed	3	10	X40CrMoV5,	220 HB	0.2	2.5	0.09	0.18	0.40	70	190	2.0	0.12	180
			10	H13, M42, D3, S6-5-2, 12Ni19	280 HB		2.5		0.16	0.40		150			140
			11		320 HB		2.0		0.14	0.32		130			120
			11		350 HB		2.0		0.14	0.26		110			110
Stainless Steel	Austenitic	4	14	304, 316, X5CrNi18-9	180 HB	0.2	2.5	0.10	0.18	0.32	170	270	2.0	0.12	260
			14		240 HB		2.5		0.18	0.26	160	220			210
	Duplex	5	14	X2CrNiN23-4, S31500	290 HB	0.2	2.0	0.09	0.14	0.20	80	150	2.0	0.12	140
			14		310 HB		2.0		0.14	0.20	70	140			140
	Ferritic & Martensitic	6	12	410, X6Cr17, 17-4 PH, 430	200 HB	0.2	2.5	0.10	0.18	0.32	170	250	2.0	0.15	240
			13		42 HRC		2.0		0.16	0.26	120	190			180
Cast Iron	Grey	7	15	GG20, GG40,	150 HB	0.2	3.0	0.08	0.20	0.64	170	250	2.0	0.18	240
			15	EN-GJL-250, No30B	200 HB		3.0		0.20	0.60	160	230			220
			16		250 HB		3.0		0.20	0.60	150	210			200
	Malleable & Nodular	8	17,19	GGG40, GGG70, 50005	150 HB	0.2	2.5	0.08	0.18	0.48	120	250	2.0	0.15	240
			17,19		200 HB		2.5		0.18	0.40		230			220
			18,20		250 HB		2.5		0.18	0.40		190			180
High Temp. Alloys	Fe, Ni & Co based	9	31,32	Incoloy 800	240 HB	0.2	2.0	0.09	0.15	0.26	25	50	2.0	0.12	40
			33	Inconel 700	250 HB		2.0		0.15	0.26	25	50			40
			34	Stellite 21	350 HB		2.0		0.15	0.26	23	45			35
	Ti based	10	36	TiAl6V4	-	0.2	2.0	0.09	0.16	0.32	45	65	2.0	0.15	60
			37	T40	-		2.0		0.14	0.26	35	60			50
Hardened Mat.	Steel	11	38	X100CrMo13, 440C,	45 HRC	0.2	1.8	0.05	0.12	0.20	50	100	1.5	0.11	90
			38	G-X260NiCr42	50 HRC		1.5		0.10	0.17	40	90	1.2	0.09	80
			38		55 HRC		1.4		0.09	0.13	40	80	1.0	0.07	70
	Chilled Cast Iron		40	Ni-Hard 2	400 HB	0.2	1.6	0.05	0.12	0.17	40	60	1.2	0.11	50
	White Cast Iron		41	G-X300CrMo15	55 HRC	0.2	1.4	0.05	0.09	0.13	30	50	1.0	0.07	40
NP	Al (>8%Si)	12	25	AlSi12	130 HB	0.2	4.0	0.10	0.30	0.70	200	400	2.0	0.20	350