

TNUX 160408 R&L LT 10 & LT 1000

Material Group	Gr. N°	VDI Group	Material Examples*	Hardness	D.O.C. [mm]		Feed [mm/rev]		Amax [mm ²]	V _c [m/min]		Optimal cutting conditions		
					min	max	min	max		min	max	D.O.C.	Feed	V _c
Steel	Non-alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.5	5.0	0.21	0.50	1.80	180	330	3.0	0.35	240
				190 HB		5.0		0.50	1.80		280			220
				250 HB		5.0		0.45	1.50		250			200
	Low alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	180 HB	0.5	5.0	0.21	0.45	1.20	120	280	3.0	0.32	200
				230 HB		4.0	0.21	0.45	1.20	120	250			180
				280 HB		4.0	0.18	0.40	1.20	120	210			150
				350 HB		3.5	0.18	0.40	1.00	120	180			130
	High alloyed	3	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.5	4.0	0.18	0.40	1.20	70	190	2.5	0.30	140
				280 HB		4.0		0.40	1.20		150			120
				320 HB		3.0		0.35	0.80		130			100
				350 HB		3.0		0.35	0.80		110			90
Stainless Steel	Austenitic	4	304, 316, X5CrNi18-9	180 HB	0.5	5.0	0.20	0.40	1.20	170	270	3.0	0.35	190
				240 HB		5.0		0.40	1.00	160	220			170
	Duplex	5	X2CrNiN23-4, S31500	290 HB	0.5	4.0	0.18	0.35	0.80	80	150	2.5	0.28	100
				310 HB		4.0		0.35	0.80	70	140			90
	Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	200 HB	0.5	5.0	0.22	0.40	1.00	170	250	3.0	0.32	190
				42 HRC		4.0		0.40	1.00	120	190			130
Cast Iron	Grey	7	GG20, GG40, EN-GJL-250, No30B	150 HB	0.5	5.0	0.15	0.60	2.00	170	250	3.0	0.35	200
				200 HB		5.0		0.60	1.80	160	230			180
				250 HB		5.0		0.55	1.80	150	210			160
	Malleable & Nodular	8	GGG40, GGG70, 50005	150 HB	0.5	5.0	0.15	0.50	1.50	120	230	3.0	0.30	160
				200 HB		5.0		0.50	1.30	190	140			
High Temp. Alloys	Fe, Ni & Co based	9	Incoloy 800, Inconel 700, Stellite 21	240 HB	0.5	3.0	0.20	0.35	0.70	25	45	2.0	0.28	32
				250 HB		3.0		0.35	0.70	25	45			30
				350 HB		3.0		0.35	0.70	23	40			28
	Ti based	10	TiAl6V4, T40	-	0.5	4.0	0.20	0.40	0.80	45	65	2.0	0.33	55
				-		3.0		0.35	0.70	35	55			45
Hardened Mat.	Steel	11	X100CrMo13, 440C, G-X260NiCr42	45 HRC	0.5	2.5	0.11	0.30	0.60	50	100	2.0	0.25	80
				50 HRC		2.0		0.25	0.40	40	90			70
				55 HRC		1.5		0.20	0.30	40	80			60
	Chilled Cast Iron	40	0.5	2.0	0.11	0.25	0.40	40	60	1.5	0.18	50		
	White Cast Iron	41	0.5	1.5	0.11	0.20	0.30	30	50	1.0	0.15	40		
Al (>8%Si)	12	25	AISI12	130 HB	0.5	6.0	0.20	0.60	1.80	200	400	3.0	0.40	280